



MIDAS WINDOW FILM™

THANKS FOR TRUSTING US!

	Visible Light Transmittance	Total Solar Transmittance	Total Solar Reflectance	Total Solar Absorbance	Visible Light Reflectance	Winter U-Value	UV Rejected	Glare Reduction	Shading Coefficient	Total Solar Energy Rejected	Film Gauge (Mils)	Structure	Peel Strength (pi)	Tensile Strength (psi)
--	-----------------------------	---------------------------	-------------------------	------------------------	---------------------------	----------------	-------------	-----------------	---------------------	-----------------------------	-------------------	-----------	--------------------	------------------------

Clear Films

2Mil	88%	75%	8%	17%	10%	1.05	99%	N/A	0.93	19%	2	1 ply	5	25,000
4Mil	86%	74%	8%	18%	10%	1.05	99%	N/A	0.92	20%	4	1 ply	5	25,000
7Mil	85%	71%	10%	19%	10%	1.05	99%	N/A	0.91	20%	7	1 ply	5	25,000
8Mil	83%	77%	8%	15%	10%	1.05	99%	N/A	0.92	19%	8	2 ply	5	25,000
11Mil	82%	70%	10%	20%	10%	1.05	99%	N/A	0.91	22%	11	2 ply	5	25,000
16Mil	82%	70%	9%	21%	10%	1.05	99%	N/A	0.9	25%	14	2 ply	5	25,000
21Mil	79%	65%	12%	23%	12%	1.01	99%	N/A	0.88	27%	21	3 ply	5	25,000

Solar Films

4Mil Titanium (SY65)	65%	54%	10%	36%	11%	14%	1.06	99%	27%	0.7	40%	4	2 ply	5	25,000
4Mil Titanium (SY35)	35%	26%	31%	43%	18%	27%	1.03	99%	58%	0.42	60%	4	3 ply	5	25,000
6Mil Titanium (SY35)	35%	26%	31%	43%	18%	27%	1.03	99%	58%	0.42	60%	6	3 ply	5	25,000
6Mil Titanium (SY25)	27%	19%	36%	45%	20%	35%	1.03	99%	70%	0.36	67%	6	3 ply	5	25,000
10Mil Titanium (SY50)	47%	34%	23%	43%	12%	16%	1.06	99%	48%	0.55	50%	10	3 ply	5	25,000
10Mil Titanium (SY35)	35%	26%	31%	43%	18%	27%	1.03	99%	58%	0.42	60%	10	3 ply	5	25,000